

# Instrumentation Tubing

## TMP Series

### Features

- ⦿ Materials: stainless steel, duplex stainless steel or nickel-based alloy
- ⦿ Sizes: 1/16" to 2" and 2 mm to 50 mm
- ⦿ Working temperature: -325°F to 1000°F (-198°C to 537°C)
- ⦿ Pickled, or bright annealed or cold worked followed by bright annealing, machined finished external surface
- ⦿ For use with FITOK 6D series tube fittings, 4:1 safety factor for the tubing and connection part of fitting and tubing
- ⦿ Marked with brand, material grade, standard, specification and heat number
- ⦿ Standard length: 40 in, 80 in, 10 ft, 20 ft, 1 m, 2 m, 3 m and 6 m  
Customized length as per customer requirement is also available



### Materials

UNS	Grade	ASTM Standard	FITOK Designator	Composition %					Mechanical Properties			
				C	Cr	Ni	Mo	Others	Yield Strength MPa	Tensile Strength MPa	Elongation %	Hardness
S31600/ S31603	316/316L	A269	SS	≤0.035 <sup>②</sup>	16-18	10-14	2.0-3.0	-	≥205	≥515	≥35	≤80 HRB
Enhanced- S31600/ S31603	Enhanced- 316/316L <sup>①</sup>		SH	≤0.03	17-18	12-14	2.6-3.0					
S30400/ S30403	304/304L		S4	≤0.035 <sup>②</sup>	18-20	8-11	-					
S31254	6Mo	A269	S12	≤0.02	19.5-20.5	17.5-18.5	6.0-6.5	-	≥310	≥675	≥35	≤96 HRB
S31803	2205	A789	D5	≤0.03	21-23	4.5-6.5	2.5-3.5	-	≥450	≥620	≥25	≤30 HRC
S32750	2507	A789	D7	≤0.03	24-26	6-8	3.0-5.0	Cu, N	≥550	≥800	≥15	≤32 HRC
N04400	Alloy 400	B165	M	≤0.30	-	≥63	-	Cu 28-34	≥195	≥480	≥35	≤75 HRB
N08020	Alloy 20	B729	A20	≤0.07	19-21	32-38	2.0-3.0	Cu, Nb, Ta	≥240	≥550	≥30	≤95 HRB
N06600	Alloy 600	B167	INC	≤0.15	14-17	≥72	-	Cu	≥205	≥550	≥35	≤92 HRB
N06625	Alloy 625	B444	A65	≤0.10	20-23	≥58	8.0-10.0	Cb, Ta	≥414	≥827	≥30	≤25 HRC
N08825	Alloy 825	B163	A85	≤0.05	19.5-23.5	38-46	2.5-3.5	Cu, Ti	≥241	≥586	≥30	≤201 HV
N10276	Alloy C-276	B622	HC	≤0.01	14.5-16.5	BAL	15.0-17.0	W	≥283	≥690	≥40	≤100 HRB

① Enhanced-316/316L complying with GB50516-2021 Technical Code for Hydrogen Fuelling Station is available, in which Ni<sub>eq</sub> is not less than 28.5%. Contact FITOK Group for more information.

② The carbon content of tubing with outside diameter smaller than 1/2" or wall thickness smaller than 0.049" is allowed up to 0.04%.

## Dimensional Tolerance

Materials	Tube O.D. (D) in. (mm)	O.D. Tolerance in. (mm)	Wall Thickness Tolerance %
316/316L Enhanced-316/316L 304/304L 6Mo	$D < 3/32$ (2.38)	+0.002 (0.05)/-0	+/-10
	$3/32$ (2.38) $\leq D < 3/16$ (4.76)	+0.003 (0.08)/-0	
	$3/16$ (4.76) $\leq D \leq 1$ (25.4)	+/-0.004 (0.10)	
	$1$ (25.4) $< D \leq 1\ 1/2$ (38.1)	+/-0.005 (0.13)	
	$1\ 1/2$ (38.1) $< D < 2$ (50.8)	+/-0.008 (0.2)	
	$D \geq 2$ (50.8)	+/-0.010 (0.25)	
2205 2507	$D < 1/2$ (12.7)	+/-0.005 (0.13)	+/-15
	$1/2$ (12.7) $\leq D \leq 3/4$ (19.05)		+/-10
Alloy 400 Alloy 20	$D < 5/8$ (16)	+/-0.005 (0.13)	+/-15
	$5/8$ (16) $\leq D < 1$ (25)		+/-10
Alloy 600	$D < 5/8$ (16)	+/-0.005 (0.13)	+/-12.5
Alloy 625	$3/16$ (4.8) $\leq D < 1/2$ (12.7)	+0.004 (0.10)/-0	+/-10
	$D \geq 1/2$ (12.7)	+0.005 (0.13)/-0	
Alloy 825	$D \leq 1/2$ (12.7)	+0.005 (0.13)/-0	+/-12.5
Alloy C-276		+/-0.005 (0.13)	

## Working Pressure at Ambient Temperature

Working pressures in the table below apply only to 316/316L, enhanced-316/316L and 304/304L. For working pressures of other materials, please contact FITOK Group or our authorized distributors.

For seamless tubing, working pressures are calculated in accordance with ASME B31.3; for single butt weld tubing, multiply the pressure rating by 0.8.

### Fractional

Tube O.D. in.	Wall Thickness in.																
	0.010	0.012	0.014	0.016	0.020	0.028	0.035	0.049	0.065	0.083	0.095	0.109	0.120	0.134	0.156	0.188	
	Working Pressure psig																
1/16	5600	6800	8100	9400	12000												
1/8						8500	10900										
3/16						5400	7000	10200									
1/4						4000	5100	7500	10200								
5/16							4000	5800	8000								
3/8							3300	4800	6500	7500							
1/2							2600	3700	5100	6700							
5/8								2900	4000	5200	6000						
3/4								2400	3300	4200	4900	5800					
7/8								2000	2800	3600	4200	4800					
1									2400	3100	3600	4200	4700				
1 1/4										2400	2800	3300	3600	4100	4900		
1 1/2											2300	2700	3000	3400	4000	4900	
2												2000	2200	2500	2900	3600	

Note: For gas service, select a tube thickness outside of the shaded area when the tube is used with 6D series tube fittings.

**Metric**

Tube O.D. mm	Wall Thickness mm													
	0.8	1.0	1.2	1.5	1.8	2.0	2.2	2.5	2.8	3.0	3.5	4.0	4.5	5.0
	Working Pressure bar													
3	670													
6	310	420	540	710										
8		310	390	520										
10		240	300	400	510	580								
12		200	250	330	410	470								
14		160	200	270	340	380	430							
15		150	190	250	310	360	400							
16			170	230	290	330	370	400						
18			150	200	260	290	320	370						
20			140	180	230	260	290	330	380					
22			140	160	200	230	260	300	340					
25					180	200	230	260	290	320				
28						180	200	230	260	280	330			
30						170	180	210	240	260	310			
32						160	170	200	220	240	290	330		
38							140	160	190	200	240	270	310	
50										150	180	210	240	270

Note: For gas service, select a tube thickness outside of the shaded area when the tube is used with 6D series tube fittings.

**Elevated Temperature Factors**

Temperature		Factor	
°F	°C	316/316L and Enhanced-316/316L	304/304L
200	93	1.00	1.00
400	204	0.96	0.93
600	315	0.85	0.82
800	426	0.79	0.76
1000	537	0.76	0.69